


DATA SHEET

KRS 9



COPMPOUND REFERENCE: EPS 0.6

MATERIAL: Closed Cell Expanded EPDM

SPECIFICATION: ATSM D1056, RE43, B2, C1

| TEST METHOD | SPECIFICATION | ACTUAL VALUES |
|---------------------------------|-------------------------------|------------------------|
| Density | 0.55 – 0.65 g/cm ₃ | 0.59 g/cm ₃ |
| B2 | | |
| Compression Set 22 Hrs @ R.T | 50% Deflection 25% Max. | 18% |
| C1 | | |
| Weather Resistance | No Cracks | No Cracks |
| Compression Deflection | 25% 11 (+ / - 2 PSI) | 10 PSI |
| Heat aging 7 days @ 70°C | | |
| Deflection Change | +/- 30% | + 15% |



T: 01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk

