


DATA SHEET

PRODUCT

KRE 717



DESCRIPTION: Crystal PVC Compound

PROPERTY	TYPICAL RESULT	TEST METHOD
BSS	38°	BS 2782356A 6mm Thick Test Piece
SHORE A	78°	ASTM D2240
SPECIFIC GRAVITY	1.23	DENSITY BALANCE
ELONGATION AT BREAK	300%	BS 2782 320A
TENSILE STRENGTH	16.5 MPa	BS 2782 320A
COLD BLEND TEMPERATURE	-35°c	BS 2782 151A
CONGO RED STABILITY @ 180°c	90 Mins Minimum	BS 2782 Part 1 Method 130A

THIS DATA SHOWS TYPICAL VALUES AND IS BELIEVED TO BE ACCURATE, HOWEVER NO WARRANTY IS GIVEN AND THESE VALUES SHOULD NOT BE TAKEN AS A SPECIFICATION



T:01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk

