


DATA SHEET

KR 035



Compound: ES60 / 13

EPDM rubber, 60 Shore A, solid, black, sulphur cured

Properties	Method	Unit	Result
Density (SG)			1.287
Hardness	IRHD	SH A	72.4
Tensile Strength		MPa	8.21
Elongation at Break		%	487.1
Ozone Resistance			Pass
UV Resistance			Pass

**THE PHYSICAL PROPERTIES HAVE BEEN DETERMINED ON PRESS PLATES
CURED 20 MINUTES AT 160°C**

Page

1 of 2




T:01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk



DATA SHEET

KR 035



Compound: ES06 / 22

EPDM sponge rubber, sulphur cured

Properties	Method	Unit	Result
Density (SG)			0.694
Tensile Strength		MPa	3.01
Elongation at break		%	361.3
Ozone Resistance			PASS
UV Resistance			PASS
<u>H2O – 168 HRS @ 23°C</u>			
Volume Change		%	-1.31
Water Absorption			+0.11
Low Temperature Properties (Gehman)		MPa @ -42°C	4.3 (Flexible)

**THE PHYSICAL PROPERTIES HAVE BEEN DETERMINED BY BEING
EXTRUDED AND THEN BLOWN 5 MINUTES @ 220°C**

Page

2 of 2



T: 01527 570570 F: 01527 575200

W: www.kingfisherrubber.co.uk

E: sales@kingfisherrubber.co.uk

