


DATA SHEET

KRE 751



EPDM 70 Shore

| Test Method | Actual Values |
|--|---------------------------|
| Hardness (IRHD) | 71 |
| Tensile Strength (MPA) | 9 |
| Elongation @ Break (%) | 150 |
| Tear Strength kN/m | 17 |
| Compression Set (22 Hrs @ 70°C) | 20 |
| O-Zone Resistance (72 Hrs @ 40°C) | 25 PPHM 20% Ext Cracks |
| AGED 70 Hrs @ 70°C | |
| Hardness Change (IRHD) | +7 |
| Tensile Change (%) | -18 |
| Elongation @ Break | -18 |
| Temperature Range | -20°C to +90°C |
| <i>This information is given to the best of our knowledge. All test data are average values and should be considered as guidelines only.</i> | |



T:01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk

