


DATA SHEET

KR 116

EPDM Solid: ASTM D2000 M1AA 707

EPDM Sponge: SAE J18B



TEST	SPEC	FREQUENCY
<i>Tensile Strength</i>	>10	<i>Monthly</i>
<i>Elongation at Break</i>	>250	<i>Monthly</i>
<i>Compression Set</i>	<50	<i>Monthly</i>
<i>Hardness</i>	65-75	<i>Monthly</i>
<i>Specific Gravity</i>	1.19-1.29	<i>Monthly</i>
<i>Tear Strength</i>	750	<i>Monthly</i>
<i>Aged Hardness</i>	+/- 10	<i>Every 3 Months</i>
<i>Aged Tensile Strength</i>	+/-15%	<i>Every 3 Months</i>
<i>Aged Elongation at Break</i>	<-50%	<i>Every 3 Months</i>
<i>Paint Staining</i>	None	<i>Yearly</i>
<i>Ozone</i>	No Cracks	<i>Yearly</i>



T:01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk

