


DATA SHEET



KR 006

Material Description: Closed Cell Expanded EPDM

Material Specification: ASTM D1056, RE43, B2, C1

TEST METHOD	SPEC	ACTUAL VALUES
Density	0.55 – 0.65g/cm ³	0.69g/cm ³
B2		
Compression Set 22 hrs @ R.T	50% Deflection 25% Max	18%
C1		
Weather Resistance	No Cracks	No Cracks
Compression Deflection	25% Deflection 11 +/- 2 PSI	10 PSI
Heat Aging – 7 Days @ 70°C Deflection Change	+/- 30%	15%



T:01527 570570 F: 01527 575200
W: www.kingfisherrubber.co.uk
E: sales@kingfisherrubber.co.uk

