


# DATA SHEET

## KRE 749



## EPDM 70 Shore

Test Method	Actual Values
Hardness (IRHD)	71
Tensile Strength (MPA)	9
Elongation @ Break (%)	150
Tear Strength kN/m	17
Compression Set (22 Hrs @ 70°C)	20
O-Zone Resistance (72 Hrs @ 40°C)	25 PPHM 20% Ext Cracks
<b>AGED 70 Hrs @ 70°C</b>	
Hardness Change (IRHD)	+7
Tensile Change (%)	-18
Elongation @ Break	-18
Temperature Range	-20°C to +90°C
<i>This information is given to the best of our knowledge. All test data are average values and should be considered as guidelines only.</i>	



T:01527 570570 F: 01527 575200  
W: [www.kingfisherrubber.co.uk](http://www.kingfisherrubber.co.uk)  
E: [sales@kingfisherrubber.co.uk](mailto:sales@kingfisherrubber.co.uk)

